

CMC SOLUTION

LET THIS STAND FOR 24 HOURS

1 gallon batch

CMC	300 grams
Water	1 gallon

1 pint batch

CMC	38 grams
Water	1 pint

100 ml. batch

CMC	8 grams
Water	100 ml.

1.5 % solution in glaze

100 gr.	Dry glaze
1.5 gr.	CMC
70 ml.	Water

THIS IS USED AS A GLAZE AND STAIN BINDER. CAN BE THINED WITH DOUBLE THE WATER TO MAKE A SPRAY SOLUTION TO HARDEN A GLAZE SURFACE FOR ON-GLAZE BRUSH PAINTING (MAJOLICA).